



West Virginia Department of Transportation

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 07

Plant Name: ACX1.01.601 Central Supply F-8 @ Buckhannon

Last Inspection: 03/08/2019

Sticker Expires: 9/8/2019

Standard Deviation: 683.21

Rating: A-1

----- Evaluation of Cement Requirements -----

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1434200	601.002.003 Concrete, Class B		2.87	2.87	27	3000	1.507	3.034	664.77	4001.81 <	4868.15 <	5016.91
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												
1434200	601.002.003 Concrete, Class B		2.87	2.63	16	3000	1.543	3.233	471.37	6043.75 >	4523.94 =	0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												
1434200	601.002.003 Concrete, Class B		2.87	2.87	36	3000	1.5	3	758.43	4137.64 <	4813.89 <	5275.29
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

----- Evaluation of Cement Requirements -----

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Less than 2 inches												
1434211	601.002.001 Concrete, Class A		3.47	3.47	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last Two Years of Data Slump Greater than or equal to 2 inches												
1434211	601.002.001 Concrete, Class A		3.47	3.47	11	3500	1.588	3.51	1102.13	5250.18 <	6021.45 <	7368.48
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last One Year of Data Slump Less than 2 inches												
1434213	601.002.003 Concrete, Class B		2.87	2.87	3							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Greater than or equal to 2 inches												
1434213	601.002.003 Concrete, Class B		2.87	2.87	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Three Months of Data Slump Greater than or equal to 2 inches												
1434213	601.002.003 Concrete, Class B		2.87	2.63	19	3000	1.528	3.151	623.36	5582.63	> 4964.21	= 0.24
					DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1434217	601.002.015 Concrete, Class K		3.35	3.35	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1434225	601.002.004 Concrete, Class B Modified		3.35	3.35	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1434229	601.002.016 Concrete, Class K Modified		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1434233	601.002.011 Concrete, Class D		2.04	2.04	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1436388	601.002.015 Concrete, Class K		3.35	3.35	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1436444	601.002.013 Concrete, Class H		3.45	3.45	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455043	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1459838	601.002.003 Concrete, Class B		2.86	2.86	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1459842	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461801	679.002.002 Concrete, Microsilica		3.82	3.82	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463308	601.002.001 Concrete, Class A	03/09/2019	3.49	3.49	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463317	601.002.015 Concrete, Class K	03/09/2019	3.37	3.37	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463322	601.002.003 Concrete, Class B	03/09/2019	2.88	2.88	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 02

Plant Name: ATA1.01.601 Adams Trucking And Supply @ Barboursville, W

Last Inspection: 02/06/2019

Sticker Expires: 8/6/2019

Standard Deviation: 481.43

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Two Years of Data Slump Greater than or equal to 2 inches

1424602	601.002.003 Concrete, Class B		2.87	2.87	4							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last One Year of Data Slump Greater than or equal to 2 inches

1424602	601.002.003 Concrete, Class B		2.87	2.87	4							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Two Years of Data Slump Greater than or equal to 2 inches

1424606	601.002.013 Concrete, Class H		3.35	3.35	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1424607	601.002.015 Concrete, Class K	03/20/2019	3.36	3.36	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 09 Plant Name: BMC1.01.601 Central Supply F-9 @ Summersville, WV
 Last Inspection: 06/03/2019 Sticker Expires: 12/3/2019 Standard Deviation: 960.48 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1432574	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1432590	601.002.003 Concrete, Class B	06/19/2019	2.87	2.87	20	3000	1.525	3.13	1021.17	4557.28	< 4998	< 6196.26
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Less than 2 inches												
1434175	601.002.015 Concrete, Class K		3.35	3.35	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436429	501.002.001 Concrete, Pavement	07/02/2017	3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436461	601.002.023 Concrete, Class H-IC	02/11/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436465	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1459809	601.002.001 Concrete, Class A		3.60	3.60	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461848	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor (K_1)	Factor (K_2)	Standard Deviation (s)	(F_c+K_1s)	Average Strength(X)	(F_c+K_2s)
1463336	601.002.003 Concrete, Class B		2.87	2.87	0	MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 10

Plant Name: BMC1.02.601 Central Supply F-10 @ Wolfpen, WV

Last Inspection: 11/14/2018

Sticker Expires: 5/14/2019

Standard Deviation: 650.00

Rating: B

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last One Year of Data Slump Greater than or equal to 2 inches

1432577	601.002.003 Concrete, Class B		2.87	2.87	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last One Year of Data Slump Less than 2 inches

1434170	601.002.015 Concrete, Class K		3.35	3.35	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last One Year of Data Slump Greater than or equal to 2 inches

1434170	601.002.015 Concrete, Class K		3.35	3.35	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1436468	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last One Year of Data Slump Greater than or equal to 2 inches

1436469	601.002.013 Concrete, Class H		3.45	3.45	4							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1455007	601.002.022 Concrete, Class DC		3.61	3.61	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1463203	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1463303	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor (K_1)	Factor (K_2)	Standard Deviation (s)	(F_c+K_1s)	Average Strength(X)	(F_c+K_2s)
1465014	601.002.013 Concrete, Class H		3.35	3.35	0	MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 10

Plant Name: BMC1.03.601 Central Supply F-11 @ Princeton, WV

Last Inspection: 05/15/2019

Sticker Expires: 11/15/2019

Standard Deviation: 637.71

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1432575	601.002.003		2.87	2.63	20	3000	1.525	3.13	498.29	4910	> 4559.65	= 0.24
	Concrete, Class B				DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							
Last One Year of Data Slump Less than 2 inches												
1432575	601.002.003		2.87	2.87	5							
	Concrete, Class B				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Greater than or equal to 2 inches												
1432575	601.002.003		2.87	2.63	85	3000	1.5	3	684.62	5418.24	> 5053.86	= 0.24
	Concrete, Class B				DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							
Last Three Months of Data Slump Greater than or equal to 2 inches												
1432575	601.002.003		2.87	2.87	3							
	Concrete, Class B				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last One Year of Data Slump Greater than or equal to 2 inches												
1434168	601.002.015		3.35	3.35	2							
	Concrete, Class K				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last One Year of Data Slump Greater than or equal to 2 inches

1434181	601.002.003 Concrete, Class B		2.87	2.87	80	3000	1.5	3	660.72	3991.08 <	4271.96 <	4982.16
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

Last One Year of Data Slump Greater than or equal to 2 inches

1434181	601.002.003 Concrete, Class B		2.87	2.87	80	3000	1.5	3	660.72	3991.08 <	4271.96 <	4982.16
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1436467	601.002.013 Concrete, Class H		3.45	3.45	6							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1455001	601.002.013 Concrete, Class H	05/13/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1455005	601.002.022 Concrete, Class DC		3.61	3.37	13	4500	1.565	3.365	693.85	7430 >	6834.81 =	0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Three Months of Data Slump Greater than or equal to 2 inches												
1463301	601.002.003 Concrete, Class B		2.87	2.87	2							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463344	601.002.013 Concrete, Class H		3.45	3.45	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 10 Plant Name: BMC1.04.601 Central Supply F-12 @ Bluefield, WV
 Last Inspection: 05/15/2019 Sticker Expires: 11/15/2019 Standard Deviation: 650.00 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1432576	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1434169	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1434182	601.002.003 Concrete, Class B		2.87	2.87	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last One Year of Data Slump Less than 2 inches												
1434182	601.002.003 Concrete, Class B		2.87	2.87	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last One Year of Data Slump Greater than or equal to 2 inches												
1434182	601.002.003 Concrete, Class B		2.87	2.87	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1436487	601.002.013 Concrete, Class H	05/13/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455006	601.002.022 Concrete, Class DC		3.61	3.61	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Three Months of Data Slump Greater than or equal to 2 inches												
1463302	601.002.003 Concrete, Class B		2.87	2.87	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1465013	601.002.013 Concrete, Class H		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 09 Plant Name: BMC1.05.601 Central Supply F-13 @ Alta, WV

Last Inspection: 06/05/2019 Sticker Expires: 12/5/2019 Standard Deviation: 923.44 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Two Years of Data Slump Greater than or equal to 2 inches

1432591	601.002.003 Concrete, Class B	06/19/2019	2.87	2.87	6							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last One Year of Data Slump Greater than or equal to 2 inches

1432591	601.002.003 Concrete, Class B	06/19/2019	2.87	2.87	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Less than 2 inches

1434176	601.002.015 Concrete, Class K		3.35	3.35	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last Two Years of Data Slump Greater than or equal to 2 inches

1434176	601.002.015 Concrete, Class K		3.35	3.35	10	4000	1.604	3.615	1033.9	5658.38	< 7438	< 7737.55
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

Last One Year of Data Slump Greater than or equal to 2 inches

1434176	601.002.015 Concrete, Class K		3.35	3.35	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1434221	601.002.003 Concrete, Class B		2.87	2.87	8							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

Last One Year of Data Slump Greater than or equal to 2 inches

1434221	601.002.003 Concrete, Class B		2.87	2.87	9							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1436430	501.002.001 Concrete, Pavement	07/02/2017	3.35	3.35	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1436459	601.002.023 Concrete, Class H-IC	02/19/2018	3.45	3.45	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1436466	601.002.013 Concrete, Class H		3.45	3.45	5							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last One Year of Data Slump Greater than or equal to 2 inches

1436466	601.002.013 Concrete, Class H		3.45	3.45	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1459801	679.002.002 Concrete, Microsilica		3.82	3.82	7							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1459810	601.002.002 Concrete, Class A Modified		3.60	3.60	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1461849	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor ($K1$)	Factor ($K2$)	Standard Deviation (s)	(F_c+K1s)	Average Strength(X)	(F_c+K2s)
1463335	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor ($K1$)	Factor ($K2$)	Standard Deviation (s)	(F_c+K1s)	Average Strength(X)	(F_c+K2s)
1465019	601.002.004 Concrete, Class B Modified		3.12	3.12	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 10 Plant Name: BMC1.06.601 Central Supply F-14 @ Beckley, WV
 Last Inspection: 05/15/2019 Sticker Expires: 11/15/2019 Standard Deviation: 698.00 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1424532	679.002.002 Concrete, Microsilica		3.82	2.87	144	3000	1.5	3	821.54	4232.31	< 4588.89	< 5464.62
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1432573	601.002.003 Concrete, Class B		2.87	2.87	20	3000	1.525	3.13	957.83	4460.69	< 4911	< 5998.01
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												
1432573	601.002.003 Concrete, Class B		2.87	2.87	144	3000	1.5	3	821.54	4232.31	< 4588.89	< 5464.62
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												
1432573	601.002.003 Concrete, Class B		2.87	2.87	10	3000	1.604	3.615	511.68	3820.73	< 4582	< 4849.72
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												
1432573	601.002.003 Concrete, Class B		2.87	2.87	100	3000	1.5	3	563.48	3845.22	< 4511.23	< 4690.44
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1432589	601.002.003 Concrete, Class B	06/19/2019	2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Less than 2 inches

1434174	601.002.015 Concrete, Class K		3.35	3.35	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last Two Years of Data Slump Greater than or equal to 2 inches

1434174	601.002.015 Concrete, Class K		3.35	3.35	6							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1436428	501.002.001 Concrete, Pavement	07/02/2017	3.35	3.35	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1436460	601.002.023 Concrete, Class H-IC	02/14/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1436464	601.002.013 Concrete, Class H		3.45	3.45	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436486	601.002.013 Concrete, Class H	05/13/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1459808	601.002.001 Concrete, Class A		3.60	3.60	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1459829	501.002.003 Concrete, Roller Compacted		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1459835	601.002.004 Concrete, Class B Modified	06/06/2019	3.24	3.24	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last One Year of Data Slump Greater than or equal to 2 inches												
1459835	601.002.004 Concrete, Class B Modified	06/06/2019	3.24	3.24	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461847	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last One Year of Data Slump Greater than or equal to 2 inches												
1463298	601.002.003 Concrete, Class B		2.87	2.87	13	3000	1.565	3.365	773.12	4209.93	< 5181.92	< 5601.55
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												
Last Three Months of Data Slump Less than 2 inches												
1463298	601.002.003 Concrete, Class B		2.87	2.87	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last Three Months of Data Slump Greater than or equal to 2 inches												
1463298	601.002.003 Concrete, Class B		2.87	2.63	17	3000	1.538	3.202	449.69	5117.65	> 4439.91	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 03 Plant Name: CCC1.01.601 Cardinal Concrete F-1 @ Ravenswood, WV
 Last Inspection: 06/26/2019 Sticker Expires: 12/26/2019 Standard Deviation: 639.39 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1398978	601.002.013 Concrete, Class H	12/29/2018	3.23	3.23	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1436396	601.002.003 Concrete, Class B		2.87	2.87	8							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						
Last One Year of Data Slump Greater than or equal to 2 inches												
1436396	601.002.003 Concrete, Class B		2.87	2.87	2							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455072	601.002.022 Concrete, Class DC	06/21/2019	3.74	3.74	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461784	679.002.002 Concrete, Microsilica		3.85	3.85	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461812	601.002.003 Concrete, Class B		2.87	2.63	28	3000	1.505	3.024	535.46	5256.43	> 4619.23	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												
1461812	601.002.003 Concrete, Class B		2.87	2.63	54	3000	1.5	3	705.93	5120.74	> 5117.79	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461816	601.002.015 Concrete, Class K		3.36	3.36	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461820	601.002.022 Concrete, Class DC		3.74	3.74	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor (K_1)	Factor (K_2)	Standard Deviation (s)	Average Strength(X)	(F_c+K_2s)	$X-(F_c+K_1s)/1.4$
1461854	601.002.013 Concrete, Class H		3.45	3.45	0	MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 03 Plant Name: CCC1.02.601 Cardinal Concrete F-2 @ Parkersburg, WV
 Last Inspection: 06/27/2019 Sticker Expires: 12/27/2019 Standard Deviation: 770.29 Rating: A-2

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Less than 2 inches												
1432578	601.002.003 Concrete, Class B	06/07/2019	2.92	2.92	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Two Years of Data Slump Greater than or equal to 2 inches												
1432578	601.002.003 Concrete, Class B	06/07/2019	2.92	2.68	37	3000	1.5	3	781.44	5506.76	> 5344.32	= 0.24
					DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							
Last One Year of Data Slump Greater than or equal to 2 inches												
1432578	601.002.003 Concrete, Class B	06/07/2019	2.92	2.92	27	3000	1.507	3.034	718.65	4083.01	< 4390.74	< 5180.38
					MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1432579	601.002.003 Concrete, Class B	06/07/2019	2.89	2.89	7							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Greater than or equal to 2 inches												
1432579	601.002.003 Concrete, Class B	06/07/2019	2.89	2.89	3							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1455049	601.002.015 Concrete, Class K	02/11/2019	3.59	3.59	4							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1459845	601.002.013 Concrete, Class H	12/29/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461785	679.002.002 Concrete, Microsilica		3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last One Year of Data Slump Greater than or equal to 2 inches												
1461813	601.002.003 Concrete, Class B		2.87	2.87	7							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last Three Months of Data Slump Greater than or equal to 2 inches												
1461813	601.002.003 Concrete, Class B		2.87	2.87	6							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461817	601.002.015 Concrete, Class K		3.36	3.36	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor ($K1$)	Factor ($K2$)	Standard Deviation (s)	(F_c+K1s)	Average Strength(X)	(F_c+K2s)
1461821	601.002.022 Concrete, Class DC		3.74	3.74	0	MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 04 Plant Name: CCC1.03.601 Cardinal Concrete F-3 @ Bridgeport, WV
 Last Inspection: 03/18/2019 Sticker Expires: 9/18/2019 Standard Deviation: 634.62 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Less than 2 inches												
1434187	601.002.003 Concrete, Class B		2.87	2.87	5							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Two Years of Data Slump Greater than or equal to 2 inches												
1434187	601.002.003 Concrete, Class B		2.87	2.87	65	3000	1.5	3	666.09	3999.14	< 4828.55	< 4998.27
					MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							
Last One Year of Data Slump Greater than or equal to 2 inches												
1434187	601.002.003 Concrete, Class B		2.87	2.63	39	3000	1.5	3	416.47	4512.03	> 4249.41	= 0.24
					DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							
Last Three Months of Data Slump Greater than or equal to 2 inches												
1434187	601.002.003 Concrete, Class B		2.87	2.87	4							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1434188	601.002.015 Concrete, Class K		3.35	3.35	5							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Less than 2 inches												
1434188	601.002.015 Concrete, Class K		3.35	3.35	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Greater than or equal to 2 inches												
1434188	601.002.015 Concrete, Class K		3.35	3.35	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Three Months of Data Slump Greater than or equal to 2 inches												
1434188	601.002.015 Concrete, Class K		3.35	3.35	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1436458	601.002.004 Concrete, Class B Modified	01/28/2018	3.35	3.35	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1455051	601.002.013 Concrete, Class H		3.45	3.45	7							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Greater than or equal to 2 inches												
1455051	601.002.013 Concrete, Class H		3.45	3.45	9							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Three Months of Data Slump Greater than or equal to 2 inches												
1455051	601.002.013 Concrete, Class H		3.45	3.45	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1455080	601.002.022 Concrete, Class DC		3.74	3.74	16	4500	1.543	3.233	807.55	5746.05	< 6641.25	< 7110.81
					MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							
Last One Year of Data Slump Greater than or equal to 2 inches												
1455080	601.002.022 Concrete, Class DC		3.74	3.74	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461786	679.002.002 Concrete, Microsilica		3.83	3.83	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor (K_1)	Factor (K_2)	Standard Deviation (s)	(F_c+K_1s)	Average Strength(X)	(F_c+K_2s)
1461822	601.002.022 Concrete, Class DC		3.74	3.74	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor (K_1)	Factor (K_2)	Standard Deviation (s)	(F_c+K_1s)	Average Strength(X)	(F_c+K_2s)
Last One Year of Data Slump Greater than or equal to 2 inches												
1461855	601.002.022 Concrete, Class DC		3.74	3.74	3							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 04

Plant Name: CSC1.01.601 Central Supply F-1 @ Saltwell, WV

Last Inspection: 03/06/2019

Sticker Expires: 9/6/2019

Standard Deviation: 640.88

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1432544 601.002.013 **05/09/2019** 3.45 3.45 6
 Concrete, Class H

MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last One Year of Data Slump Greater than or equal to 2 inches

1432553 679.002.002 **05/09/2019** 3.82 3.82 2
 Concrete, Microsilica

MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Three Months of Data Slump Greater than or equal to 2 inches

1434196 601.002.003 2.87 2.87 7
 Concrete, Class B

MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1434198 601.002.003 2.87 2.87 0
 Concrete, Class B

MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Less than 2 inches												
1434199	601.002.003 Concrete, Class B		2.87	2.87	6							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Two Years of Data Slump Greater than or equal to 2 inches												
1434199	601.002.003 Concrete, Class B		2.87	2.87	120	3000	1.5	3	643.52	3965.28	< 4856.26	< 4930.56
					MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							
Last One Year of Data Slump Less than 2 inches												
1434199	601.002.003 Concrete, Class B		2.87	2.63	10	3000	1.604	3.615	665.02	6187	> 5404.05	= 0.24
					DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							
Last One Year of Data Slump Greater than or equal to 2 inches												
1434199	601.002.003 Concrete, Class B		2.87	2.63	35	3000	1.5	3	477.06	4450.6	> 4431.18	= 0.24
					DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1436403	601.002.015 Concrete, Class K		3.35	3.35	12	4000	1.576	3.429	669.68	5055.42	< 5292.5	< 6296.33
					MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							
Last One Year of Data Slump Greater than or equal to 2 inches												
1436403	601.002.015 Concrete, Class K		3.35	3.35	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436405	601.002.015 Concrete, Class K		3.35	3.35	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1436419	601.002.001 Concrete, Class A		3.47	3.47	3							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1436462	601.002.023 Concrete, Class H-IC	03/25/2018	3.45	3.45	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1455036	601.002.022 Concrete, Class DC		3.58	3.58	4							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1458960	601.002.016 Concrete, Class K Modified		3.47	3.47	3							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

Last One Year of Data Slump Greater than or equal to 2 inches

1458960	601.002.016 Concrete, Class K Modified		3.47	3.47	5							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463247	601.002.001 Concrete, Class A		3.47	3.47	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463248	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463249	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463250	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463251	601.002.013 Concrete, Class H		3.47	3.47	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463312	601.002.015 Concrete, Class K		0	0	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463313	601.002.003 Concrete, Class B		2.88	2.88	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 04

Plant Name: CSC1.02.601 Central Supply F-2 @ Westover, WV

Last Inspection: 03/07/2019

Sticker Expires: 9/7/2019

Standard Deviation: 664.71

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last One Year of Data Slump Greater than or equal to 2 inches

1432523	601.002.003 Concrete, Class B		2.87	2.87	3							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

Last Three Months of Data Slump Greater than or equal to 2 inches

1432523	601.002.003 Concrete, Class B		2.87	2.87	3							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1432547	601.002.013 Concrete, Class H		3.45	3.45	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1432552	679.002.002 Concrete, Microsilica	05/09/2019	3.82	3.82	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Three Months of Data Slump Greater than or equal to 2 inches												
1434192	601.002.003		2.87	2.87	1							
	Concrete, Class B											
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Less than 2 inches												
1434193	601.002.003		2.87	2.87	9							
	Concrete, Class B											
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last Two Years of Data Slump Greater than or equal to 2 inches												
1434193	601.002.003		2.87	2.87	58	3000	1.5	3	755.67	4133.5	< 5157.74	< 5267.01
	Concrete, Class B											
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												
Last One Year of Data Slump Less than 2 inches												
1434193	601.002.003		2.87	2.63	15	3000	1.549	3.27	661.41	5765.73	> 5162.81	= 0.24
	Concrete, Class B											
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												
Last One Year of Data Slump Greater than or equal to 2 inches												
1434193	601.002.003		2.87	2.63	18	3000	1.533	3.175	617.58	4992.22	> 4960.82	= 0.24
	Concrete, Class B											
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1434195	601.002.001		3.47	3.47	0							
	Concrete, Class A											
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1436404	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436406	601.002.015 Concrete, Class K		3.35	3.35	41	4000	1.5	3	686.52	5029.78	< 5870.39	< 6059.56
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436463	601.002.023 Concrete, Class H-IC	03/26/2018	3.44	3.44	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1455037	601.002.022 Concrete, Class DC		3.58	3.58	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1458961	601.002.016 Concrete, Class K Modified		3.47	3.47	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1459833	501.002.003 Concrete, Roller Compacted		2.87	2.87	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1463260	601.002.015 Concrete, Class K		3.35	3.35	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Three Months of Data Slump Greater than or equal to 2 inches

1463267	601.002.003 Concrete, Class B		2.87	2.87	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463286	601.002.013 Concrete, Class H		3.47	3.47	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463287	601.002.001 Concrete, Class A		3.47	3.47	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463288	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463310	601.002.015 Concrete, Class K		3.37	3.37	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 08

Plant Name: CSC1.03.601 Central Supply F-3 @ Elkins, WV

Last Inspection: 03/05/2019

Sticker Expires: 9/5/2019

Standard Deviation: 643.48

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Less than 2 inches												
1434201	601.002.003 Concrete, Class B		2.87	2.87	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Two Years of Data Slump Greater than or equal to 2 inches												
1434201	601.002.003 Concrete, Class B		2.87	2.87	60	3000	1.5	3	679.71	4019.56 <	4695.17 <	5039.13
					MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							
Last One Year of Data Slump Less than 2 inches												
1434201	601.002.003 Concrete, Class B		2.87	2.87	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Greater than or equal to 2 inches												
1434201	601.002.003 Concrete, Class B		2.87	2.87	67	3000	1.5	3	716.77	4075.16 <	4920 <	5150.31
					MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							
Last Three Months of Data Slump Greater than or equal to 2 inches												
1434201	601.002.003 Concrete, Class B		2.87	2.63	10	3000	1.604	3.615	605.76	5409 >	5189.82 =	0.24
					DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1434212	601.002.001 Concrete, Class A		3.47	3.47	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Greater than or equal to 2 inches												
1434212	601.002.001 Concrete, Class A		3.47	3.47	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Three Months of Data Slump Greater than or equal to 2 inches												
1434214	601.002.003 Concrete, Class B		2.87	2.87	7							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Three Months of Data Slump Greater than or equal to 2 inches												
1434218	601.002.015 Concrete, Class K		3.35	3.35	1							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1434226	601.002.004 Concrete, Class B Modified		3.35	3.35	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1434230	601.002.016 Concrete, Class K Modified		3.35	3.35	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1434234	601.002.011 Concrete, Class D		2.04	2.04	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Less than 2 inches												
1436389	601.002.015 Concrete, Class K		3.35	3.35	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last One Year of Data Slump Less than 2 inches												
1436389	601.002.015 Concrete, Class K		3.35	3.35	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last One Year of Data Slump Greater than or equal to 2 inches												
1436389	601.002.015 Concrete, Class K		3.35	3.35	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1436443	601.002.013 Concrete, Class H		3.45	3.45	5							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last One Year of Data Slump Greater than or equal to 2 inches												
1436443	601.002.013 Concrete, Class H		3.45	3.45	6							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last Three Months of Data Slump Greater than or equal to 2 inches												
1436443	601.002.013 Concrete, Class H		3.45	3.45	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455042	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1459834	601.002.004 Concrete, Class B Modified		3.37	3.37	9							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last One Year of Data Slump Greater than or equal to 2 inches												
1459834	601.002.004 Concrete, Class B Modified		3.37	3.13	37	4000	1.5	3	605.36	6255.95	> 5816.08	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												
Last Three Months of Data Slump Greater than or equal to 2 inches												
1459834	601.002.004 Concrete, Class B Modified		3.37	3.37	4							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last One Year of Data Slump Greater than or equal to 2 inches												
1459837	601.002.003 Concrete, Class B		2.86	2.86	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1459841	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1459844	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last One Year of Data Slump Greater than or equal to 2 inches												
1461800	679.002.002 Concrete, Microsilica		3.82	3.82	8							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461824	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461826	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461828	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461830	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461832	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461845	601.002.001 Concrete, Class A		3.47	3.47	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463305	601.002.001 Concrete, Class A	03/09/2019	3.49	3.49	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463314	601.002.015 Concrete, Class K	03/09/2019	3.37	3.37	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463319	601.002.003 Concrete, Class B	03/09/2019	2.88	2.88	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor (K_1)	Factor (K_2)	Standard Deviation (s)	Average Strength(X)	(F_c+K_2s)	$X-(F_c+K_1s)/1.4$
1465016	601.002.004 Concrete, Class B Modified		2.87	2.87	0	MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 07

Plant Name: CSC1.04.601 Central Supply F-4 @ Gassaway, WV

Last Inspection: 03/11/2019

Sticker Expires: 9/11/2019

Standard Deviation: 602.75

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1434202 601.002.003 2.87 2.63 27 3000 1.507 3.034 577.79 5237.04 > 4753.01 = 0.24

Concrete, Class B

DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												
--	--	--	--	--	--	--	--	--	--	--	--	--

Last One Year of Data Slump Greater than or equal to 2 inches

1434202 601.002.003 2.87 2.87 14 3000 1.557 3.313 678.16 4055.9 < 4770.71 < 5246.74

Concrete, Class B

MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												
---	--	--	--	--	--	--	--	--	--	--	--	--

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1434215 601.002.003 2.87 2.87 0

Concrete, Class B

MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
---	--	--	--	--	--	--	--	--	--	--	--	--

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1434219 601.002.015 3.35 3.35 1

Concrete, Class K

MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
---	--	--	--	--	--	--	--	--	--	--	--	--

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1434228	601.002.004 Concrete, Class B Modified		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1434232	601.002.016 Concrete, Class K Modified		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1434235	601.002.011 Concrete, Class D		2.04	2.04	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1436390	601.002.015 Concrete, Class K		3.35	3.35	4							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436414	601.002.001 Concrete, Class A		3.47	3.47	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436446	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1455045	601.002.022 Concrete, Class DC		3.59	3.59	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1458980	679.002.002 Concrete, Microsilica		3.82	3.58	23	4000	1.515	3.081	659.42	8238.26	> 6031.67	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1459840	601.002.003 Concrete, Class B		2.86	2.86	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463307	601.002.001 Concrete, Class A	03/09/2019	3.49	3.49	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463316	601.002.015 Concrete, Class K	03/09/2019	3.37	3.37	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463321	601.002.003 Concrete, Class B	03/09/2019	2.88	2.88	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 07

Plant Name: CSC1.05.601 Central Supply F-5 @ Glenville, WV

Last Inspection: 03/11/2019

Sticker Expires: 9/11/2019

Standard Deviation: 518.14

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Two Years of Data Slump Greater than or equal to 2 inches

1434203	601.002.003 Concrete, Class B		2.87	2.87	4							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last One Year of Data Slump Greater than or equal to 2 inches

1434203	601.002.003 Concrete, Class B		2.87	2.87	14	3000	1.557	3.313	661.28	4029.61	< 4397.86	< 5190.82
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1434216	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1434220	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1434227	601.002.004 Concrete, Class B Modified		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1434231	601.002.016 Concrete, Class K Modified		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1434236	601.002.011 Concrete, Class D		2.04	2.04	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1436391	601.002.015 Concrete, Class K		3.35	3.35	4							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last One Year of Data Slump Less than 2 inches												
1436391	601.002.015 Concrete, Class K		3.35	3.35	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436415	601.002.001 Concrete, Class A		3.47	3.47	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last One Year of Data Slump Greater than or equal to 2 inches												
1436445	601.002.013 Concrete, Class H		3.45	3.45	6							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1455044	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1458979	679.002.002 Concrete, Microsilica		3.82	3.82	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1459839	601.002.003 Concrete, Class B		2.86	2.86	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1459843	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463306	601.002.001 Concrete, Class A	03/09/2019	3.49	3.49	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463315	601.002.015 Concrete, Class K	03/09/2019	3.37	3.37	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor ($K1$)	Factor ($K2$)	Standard Deviation (s)	(F_c+K1s)	Average Strength(X)	(F_c+K2s)
1463320	601.002.003 Concrete, Class B	03/09/2019	2.88	2.88	0	MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 03

Plant Name: CSC1.15.601 Central Supply F-15 @ Pennsboro, WV

Last Inspection: 03/06/2019

Sticker Expires: 9/6/2019

Standard Deviation: 673.51

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458974	601.002.001 Concrete, Class A		3.47	3.47	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458975	601.002.003 Concrete, Class B		2.87	2.87	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1458976	601.002.003 Concrete, Class B		2.86	2.86	7							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						
Last One Year of Data Slump Greater than or equal to 2 inches												
1458976	601.002.003 Concrete, Class B		2.86	2.86	5							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458977	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458978	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1459812	679.002.002 Concrete, Microsilica		3.82	3.82	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463246	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463309	601.002.001 Concrete, Class A	03/09/2019	3.49	3.49	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463318	601.002.015 Concrete, Class K	03/09/2019	3.37	3.37	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463323	601.002.003 Concrete, Class B	03/09/2019	2.88	2.88	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1464653	601.002.022 Concrete, Class DC	11/24/2018	3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 08 Plant Name: CSC1.16.601 Central Supply F-16 @ Parsons, WV
 Last Inspection: 04/18/2019 Sticker Expires: 10/18/2019 Standard Deviation: 691.58 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461825	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461827	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461829	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461831	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461833	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461835	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461836	601.002.003 Concrete, Class B		2.86	2.86	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
Last One Year of Data Slump Greater than or equal to 2 inches												
1461837	601.002.004 Concrete, Class B Modified		3.37	3.37	11	5300	1.588	3.51	743.24	6462.73	< 6480.27	= 0
INCREASE CEMENT FACTOR BY 0 PER SECTION 3.3 OF MP 711.03.26												
Last Three Months of Data Slump Greater than or equal to 2 inches												
1461837	601.002.004 Concrete, Class B Modified		3.37	3.37	4							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1461838	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1461846	601.002.001 Concrete, Class A		3.47	3.47	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1465015	601.002.004 Concrete, Class B Modified		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1465021	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 01

Plant Name: CSC2.01.601 Claxton Smith Concrete F-1 @ Poca, WV

Last Inspection: 03/12/2019

Sticker Expires: 9/12/2019

Standard Deviation: 650.00

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436435	601.002.015 Concrete, Class K	07/16/2017	3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436438	601.002.022 Concrete, Class DC	07/16/2017	3.61	3.61	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436449	601.002.013 Concrete, Class H	07/16/2017	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436474	501.002.001 Concrete, Pavement	04/21/2018	3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436477	501.002.001 Concrete, Pavement	04/20/2018	3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1455053	601.002.022 Concrete, Class DC	03/13/2019	3.74	3.74	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
Last One Year of Data Slump Greater than or equal to 2 inches												
1461805	601.002.003 Concrete, Class B		2.95	2.95	5							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 02

Plant Name: CSC2.02.601 Claxton Smith Concrete F-2 @ Culloden, WV

Last Inspection: 04/25/2019

Sticker Expires: 10/25/2019

Standard Deviation: 650.00

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436436	601.002.015 Concrete, Class K	07/16/2017	3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436439	601.002.022 Concrete, Class DC	07/16/2017	3.61	3.61	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436450	601.002.013 Concrete, Class H	07/18/2017	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436472	501.002.001 Concrete, Pavement	04/21/2018	3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436475	501.002.002 Concrete, Pavement HES	04/20/2018	3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1455054	601.002.022 Concrete, Class DC	03/13/2019	3.74	3.74	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1461804	601.002.003 Concrete, Class B		2.96	2.96	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 01

Plant Name: CSC2.03.601 Claxton Smith Concrete F-3 @ Charleston, WV

Last Inspection: 03/11/2019

Sticker Expires: 9/11/2019

Standard Deviation: 598.06

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436437	601.002.015 Concrete, Class K	07/16/2017	3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436440	601.002.022 Concrete, Class DC	07/16/2017	3.34	3.34	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436451	601.002.013 Concrete, Class H	07/18/2017	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436473	501.002.001 Concrete, Pavement	04/21/2018	3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1436476	501.002.002 Concrete, Pavement HES	04/20/2018	3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
1455055	601.002.022 Concrete, Class DC	03/13/2019	3.74	3.74	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Less than 2 inches												
1461803	601.002.003 Concrete, Class B		2.96	2.96	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last Two Years of Data Slump Greater than or equal to 2 inches												
1461803	601.002.003 Concrete, Class B		2.96	2.96	7							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last One Year of Data Slump Greater than or equal to 2 inches												
1461803	601.002.003 Concrete, Class B		2.96	2.96	25	3000	1.511	3.055	555.43	3839.25	< 4523.6	< 4696.84
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 06 Plant Name: DCC1.01.601 D.W. Dickey Concrete @ Steubenville, OH
 Last Inspection: 03/19/2019 Sticker Expires: 9/19/2019 Standard Deviation: 650.00 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last One Year of Data Slump Less than 2 inches												
1399046	601.002.003		2.87	2.87	1							
	Concrete, Class B					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						
Last One Year of Data Slump Greater than or equal to 2 inches												
1399046	601.002.003		2.87	2.87	4							
	Concrete, Class B					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

District: 05 Plant Name: DCX1.01.601 Dan Lee Co. F-1 @ Inwood, WV (Transit)
 Last Inspection: 04/03/2019 Sticker Expires: 10/3/2019 Standard Deviation: 650.00 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1458943	601.002.003		2.87	2.87	1							
	Concrete, Class B					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						
Last One Year of Data Slump Greater than or equal to 2 inches												
1458943	601.002.003		2.87	2.87	1							
	Concrete, Class B					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 10

Plant Name: DHC1.02.601 David Hill Conc. Inc F-2 @ Mabscott, WV

Last Inspection: 05/10/2019

Sticker Expires: 11/10/2019

Standard Deviation: 568.28

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1458992	601.002.003 Concrete, Class B		2.87	2.87	4							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last One Year of Data Slump Greater than or equal to 2 inches

1458992	601.002.003 Concrete, Class B		2.87	2.87	8							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last One Year of Data Slump Greater than or equal to 2 inches

1458993	601.002.015 Concrete, Class K		3.35	3.35	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1459836	601.002.022 Concrete, Class DC		3.74	3.74	7							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1461802	601.002.013 Concrete, Class H		3.45	3.45	4							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last One Year of Data Slump Greater than or equal to 2 inches

1461802	601.002.013 Concrete, Class H		3.45	3.45	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Three Months of Data Slump Greater than or equal to 2 inches

1463296	601.002.003 Concrete, Class B	06/06/2019	2.87	2.87	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1463297	601.002.013 Concrete, Class H	03/19/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1463299	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463300	601.002.015 Concrete, Class K		3.35	3.35	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 10 Plant Name: ECI1.01.601 Eastern Concrete Pinville WV
 Last Inspection: 04/15/2019 Sticker Expires: 10/15/2019 Standard Deviation: 650.00 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463324	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463325	501.002.001 Concrete, Pavement		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463326	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463327	601.002.022 Concrete, Class DC		3.74	3.74	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463328	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1465023	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1465024	501.002.001 Concrete, Pavement		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 01

Plant Name: ERM1.02.601 Hanson Ready Mix F-2 @ Gallipolis, OH

Last Inspection: 01/04/2019

Sticker Expires: 7/4/2019

Standard Deviation: 493.22

Rating: B

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1459802	601.002.013 Concrete, Class H		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1459811	601.002.003 Concrete, Class B	03/11/2019	2.87	2.87	25	3000	1.511	3.055	506.93	3765.97 <	4450.8 <	4548.67
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1459827	601.002.013 Concrete, Class H		3.45	3.45	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1459831	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461797	601.002.003 Concrete, Class B		2.87	2.87	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last One Year of Data Slump Greater than or equal to 2 inches												
1461842	601.002.015 Concrete, Class K		3.35	3.35	3							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 06 Plant Name: ERM1.03.601 Hanson Ready Mix F-3 @ New Martinsville, WV
 Last Inspection: 05/15/2019 Sticker Expires: 11/15/2019 Standard Deviation: 556.57 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Less than 2 inches

1436441	601.002.015 Concrete, Class K	07/17/2017	3.34	3.34	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last Two Years of Data Slump Greater than or equal to 2 inches

1436441	601.002.015 Concrete, Class K	07/17/2017	3.34	3.34	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1436447	601.002.003 Concrete, Class B	07/17/2017	2.87	2.87	5							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1455087	601.002.013 Concrete, Class H		3.45	3.45	5							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1455089	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458939	679.002.002 Concrete, Microsilica		3.82	3.82	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last One Year of Data Slump Less than 2 inches												
1461780	601.002.015 Concrete, Class K		3.41	3.41	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last One Year of Data Slump Greater than or equal to 2 inches												
1461780	601.002.015 Concrete, Class K		3.41	3.41	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last Three Months of Data Slump Greater than or equal to 2 inches												
1461780	601.002.015 Concrete, Class K		3.41	3.41	7							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last One Year of Data Slump Less than 2 inches												
1461798	601.002.003		2.87	2.87	2							
	Concrete, Class B				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Greater than or equal to 2 inches												
1461798	601.002.003		2.87	2.87	45	3000	1.5	3	641.5	3962.25	< 4243.33	< 4924.5
	Concrete, Class B				MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							
Last Three Months of Data Slump Greater than or equal to 2 inches												
1461798	601.002.003		2.87	2.63	21	3000	1.521	3.112	495.04	5297.14	> 4540.56	= 0.24
	Concrete, Class B				DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							

----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last One Year of Data Slump Greater than or equal to 2 inches												
1461823	601.002.022		3.75	3.75	6							
	Concrete, Class DC				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Three Months of Data Slump Greater than or equal to 2 inches												
1461823	601.002.022		3.75	3.75	3							
	Concrete, Class DC				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last One Year of Data Slump Greater than or equal to 2 inches												
1463259	601.002.013		3.45	3.45	4							
	Concrete, Class H				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 06

Plant Name: ERM1.04.601 Hanson Ready Mix F-4 @ McMechen WV

Last Inspection: 05/15/2019

Sticker Expires: 11/15/2019

Standard Deviation: 709.34

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1436442	601.002.015 Concrete, Class K	07/17/2017	3.34	3.34	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Less than 2 inches												
1436448	601.002.003 Concrete, Class B	07/17/2017	2.87	2.87	1							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						
Last Two Years of Data Slump Greater than or equal to 2 inches												
1436448	601.002.003 Concrete, Class B	07/17/2017	2.87	2.87	8							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last One Year of Data Slump Greater than or equal to 2 inches												
1461779	601.002.022 Concrete, Class DC		3.75	3.75	4							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor ($K1$)	Factor ($K2$)	Standard Deviation (s)	Average Strength(X)	(F_c+K2s)	$X-(F_c+K1s)/1.4$
Last Two Years of Data Slump Greater than or equal to 2 inches												
1461781	601.002.015		3.35	3.35	5							
	Concrete, Class K				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Less than 2 inches												
1461781	601.002.015		3.35	3.35	1							
	Concrete, Class K				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Greater than or equal to 2 inches												
1461781	601.002.015		3.35	3.35	1							
	Concrete, Class K				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor ($K1$)	Factor ($K2$)	Standard Deviation (s)	(F_c+K1s)	Average Strength(X)	(F_c+K2s)
Last Two Years of Data Slump Less than 2 inches												
1461799	601.002.003		2.87	2.87	1							
	Concrete, Class B				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Two Years of Data Slump Greater than or equal to 2 inches												
1461799	601.002.003		2.87	2.87	11	3000	1.588	3.51	633.63	4006.2	< 4742.73	< 5224.04
	Concrete, Class B				MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							
Last One Year of Data Slump Less than 2 inches												
1461799	601.002.003		2.87	2.87	4							
	Concrete, Class B				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Greater than or equal to 2 inches												
1461799	601.002.003		2.87	2.87	49	3000	1.5	3	698.5	4047.75	< 4654.29	< 5095.5
	Concrete, Class B				MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							
Last Three Months of Data Slump Greater than or equal to 2 inches												
1461799	601.002.003		2.87	2.87	1							
	Concrete, Class B				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor ($K1$)	Factor ($K2$)	Standard Deviation (s)	(F_c+K1s)	Average Strength(X)	(F_c+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	--------------------------	-----------------	-----------------	----------------------------	---------------	-------------------------	---------------

Last One Year of Data Slump Greater than or equal to 2 inches

1463258	601.002.013 Concrete, Class H		3.45	3.45	4							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

Last Three Months of Data Slump Greater than or equal to 2 inches

1463258	601.002.013 Concrete, Class H		3.45	3.45	6							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor ($K1$)	Factor ($K2$)	Standard Deviation (s)	(F_c+K1s)	Average Strength(X)	(F_c+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	--------------------------	-----------------	-----------------	----------------------------	---------------	-------------------------	---------------

1465018	601.002.013 Concrete, Class H		3.45	3.45	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 01 Plant Name: ERM1.05.601 Hanson Ready Mix F-5 @ Winfield, WV
 Last Inspection: 03/05/2019 Sticker Expires: 9/5/2019 Standard Deviation: 600.64 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1424567	601.002.004 Concrete, Class B Modified	03/11/2019	3.34	3.34	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Less than 2 inches												
1424572	601.002.003 Concrete, Class B	03/11/2019	2.87	2.87	1							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						
Last Two Years of Data Slump Greater than or equal to 2 inches												
1424572	601.002.003 Concrete, Class B	03/11/2019	2.87	2.87	85	3000	1.5	3	599.22	3898.83	< 4726.47	< 4797.66
						MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26						
Last One Year of Data Slump Greater than or equal to 2 inches												
1424572	601.002.003 Concrete, Class B	03/11/2019	2.87	2.87	1							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1424599	601.002.013 Concrete, Class H	03/19/2019	3.45	3.45	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436421	601.002.003 Concrete, Class B		2.87	2.87	10	3000	1.604	3.615	661.51	4061.06 <	5348 <	5391.36
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												
1436421	601.002.003 Concrete, Class B		2.87	2.87	66	3000	1.5	3	724.41	4086.62 <	5020.15 <	5173.23
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												
Last One Year of Data Slump Less than 2 inches												
1436421	601.002.003 Concrete, Class B		2.87	2.87	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last One Year of Data Slump Greater than or equal to 2 inches												
1436421	601.002.003 Concrete, Class B		2.87	2.87	22	3000	1.518	3.096	595.63	3904.17 <	4311.36 <	4844.07
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												
Last Three Months of Data Slump Less than 2 inches												
1436421	601.002.003 Concrete, Class B		2.87	2.87	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last Three Months of Data Slump Greater than or equal to 2 inches												
1436421	601.002.003 Concrete, Class B		2.87	2.87	6							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1436426	601.002.022 Concrete, Class DC		3.73	3.73	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1455029	601.002.014 Concrete, Class H Modified	09/03/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Less than 2 inches												
1458948	601.002.015 Concrete, Class K		3.83	3.83	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last Two Years of Data Slump Greater than or equal to 2 inches												
1458948	601.002.015 Concrete, Class K		3.83	3.83	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K1s)	(Fc+K1s)-X/1.4 Increase
Last Two Years of Data Slump Greater than or equal to 2 inches												
1459006	601.002.015 Concrete, Class K		3.39	3.39	15	4000	1.549	3.27	550.1	4852.1	< 4979.33	< 5798.83
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												
Last One Year of Data Slump Greater than or equal to 2 inches												
1459006	601.002.015 Concrete, Class K		3.39	3.39	19	4000	1.528	3.151	640.67	4738.42	< 4978.94	= 0
INCREASE CEMENT FACTOR BY 0 PER SECTION 3.3 OF MP 711.03.26												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Two Years of Data Slump Greater than or equal to 2 inches

1459828	601.002.013		3.45	3.21	38	4000	1.5	3	648.17	7351.84	> 5944.51	= 0.24
	Concrete, Class H				DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							

Last One Year of Data Slump Greater than or equal to 2 inches

1459828	601.002.013		3.45	3.21	47	4000	1.5	3	612.03	7692.55	> 5836.09	= 0.24
	Concrete, Class H				DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Two Years of Data Slump Greater than or equal to 2 inches

1459832	601.002.013		3.45	3.45	7							
	Concrete, Class H				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1461792	601.002.003		2.87	2.87	30	3000	1.501	3.008	535.68	3804.06	< 4080.33	< 4611.33
	Concrete, Class B				MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							

Last One Year of Data Slump Less than 2 inches

1461792	601.002.003		2.87	2.87	1							
	Concrete, Class B				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

Last One Year of Data Slump Greater than or equal to 2 inches

1461792	601.002.003		2.87	2.87	39	3000	1.5	3	548.46	3822.69	< 4039.49	< 4645.38
	Concrete, Class B				MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							

Last Three Months of Data Slump Greater than or equal to 2 inches

1461792	601.002.003		2.87	2.87	3							
	Concrete, Class B				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461794	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last One Year of Data Slump Less than 2 inches												
1461839	601.002.015 Concrete, Class K		3.35	3.35	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last One Year of Data Slump Greater than or equal to 2 inches												
1461839	601.002.015 Concrete, Class K		3.35	3.35	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 03

Plant Name: ERM1.06.601 Hanson Ready Mix F-6 @ Parkersburg, WV

Last Inspection: 02/14/2019

Sticker Expires: 8/14/2019

Standard Deviation: 569.21

Rating: A-2

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Less than 2 inches												
1436399	601.002.003 Concrete, Class B		2.87	2.87	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Two Years of Data Slump Greater than or equal to 2 inches												
1436399	601.002.003 Concrete, Class B		2.87	2.87	56	3000	1.5	3	677.48	4016.22	< 4160.71	< 5032.44
					MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							
Last One Year of Data Slump Greater than or equal to 2 inches												
1436399	601.002.003 Concrete, Class B		2.87	2.87	67	3000	1.5	3	458.88	3688.32	< 3995.07	< 4376.64
					MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1455027	601.002.023 Concrete, Class H-IC	09/07/2018	3.45	3.45	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1455050	601.002.022 Concrete, Class DC	02/21/2019	3.73	3.73	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1455090	601.002.013 Concrete, Class H		3.45	3.21	10	4000	1.604	3.615	759.08	6857	> 6744.07	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461834	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463257	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463304	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor (K_1)	Factor (K_2)	Standard Deviation (s)	Average Strength(X)	(F_c+K_2s)	$X-(F_c+K_1s)/1.4$
1465020	601.002.013 Concrete, Class H		3.45	3.45	0	MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 01

Plant Name: ERM1.07.601 Hanson Ready Mix F-7 @ Charleston, WV

Last Inspection: 03/15/2019

Sticker Expires: 9/15/2019

Standard Deviation: 568.51

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Less than 2 inches

1424571	601.002.003 Concrete, Class B	03/11/2019	2.87	2.87	4							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last Two Years of Data Slump Greater than or equal to 2 inches

1424571	601.002.003 Concrete, Class B	03/11/2019	2.87	2.87	18	3000	1.533	3.175	624.94	3958.03	< 4742.22	< 4984.18
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1424600	601.002.013 Concrete, Class H	02/13/2019	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1432540	679.002.002 Concrete, Microsilica		3.82	3.82	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1436420	601.002.003 Concrete, Class B		2.87	2.87	5							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436453	601.002.022 Concrete, Class DC		3.73	3.73	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436478	601.002.016 Concrete, Class K Modified	04/20/2018	4.07	4.07	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436479	601.002.015 Concrete, Class K	04/21/2018	4.07	4.07	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436480	601.002.003 Concrete, Class B		4.07	4.07	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436481	601.002.003 Concrete, Class B		4.07	4.07	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1455088	679.002.002 Concrete, Microsilica		3.82	3.82	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458950	601.002.015 Concrete, Class K		3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1459008	601.002.015 Concrete, Class K		3.39	3.39	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1459826	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1459830	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461796	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461841	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1465025	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1465026	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 02

Plant Name: ERM1.08.601 Hanson Ready Mix F-8 @ Huntington, WV

Last Inspection: 05/09/2019

Sticker Expires: 11/9/2019

Standard Deviation: 650.00

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458946	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458947	601.002.015 Concrete, Class K		3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1459005	601.002.015 Concrete, Class K		3.39	3.39	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463334	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 01

Plant Name: ERM1.09.601 Hanson Ready Mix F-9 @ Winfield, WV (Transit)

Last Inspection: 03/05/2019

Sticker Expires: 9/5/2019

Standard Deviation: 650.00

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436427	601.002.022 Concrete, Class DC	07/02/2017	3.73	3.73	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458949	601.002.015 Concrete, Class K		3.83	3.83	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last One Year of Data Slump Less than 2 inches												
1459007	601.002.015 Concrete, Class K		3.39	3.39	5							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461793	601.002.003 Concrete, Class B		2.87	2.87	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461795	601.002.015 Concrete, Class K		3.35	3.35	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1461840	601.002.015 Concrete, Class K		3.35	3.35	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 05 Plant Name: FCC1.01.601 Fairfax Concrete F-1 @ Scherr WV
 Last Inspection: 03/12/2019 Sticker Expires: 9/12/2019 Standard Deviation: 849.74 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1421095	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1421097	601.002.004 Concrete, Class B Modified	06/20/2019	3.33	3.33	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1421098	601.002.003 Concrete, Class B		2.86	2.62	10	3000	1.604	3.615	619.93	6632.2	> 5241.05	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												
1421098	601.002.003 Concrete, Class B		2.86	2.62	10	3000	1.604	3.615	678.62	6542.1	> 5453.21	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Less than 2 inches												
1421100	601.002.015 Concrete, Class K		3.33	3.33	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Two Years of Data Slump Greater than or equal to 2 inches												
1421100	601.002.015 Concrete, Class K		3.33	3.33	7							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Greater than or equal to 2 inches												
1421100	601.002.015 Concrete, Class K		3.33	3.33	8							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1421102	601.002.013 Concrete, Class H		3.44	3.2	12	4000	1.576	3.429	709.29	7720.83	> 6432.16	= 0.24
					DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							
Last One Year of Data Slump Greater than or equal to 2 inches												
1421102	601.002.013 Concrete, Class H		3.44	3.44	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1432581	601.002.003 Concrete, Class B	06/07/2019	2.87	2.87	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455035	601.002.023 Concrete, Class H-IC	10/14/2018	3.46	3.46	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455046	601.002.023 Concrete, Class H-IC	01/27/2019	3.43	3.43	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455076	601.002.003 Concrete, Class B		2.86	2.86	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463272	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last One Year of Data Slump Greater than or equal to 2 inches

1463275	601.002.003 Concrete, Class B		2.87	2.87	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1463278	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1463281	601.002.013 Concrete, Class H		3.44	3.44	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 08 Plant Name: FCC1.02.601 Fairfax Concrete F-2 @ Oakland, MD
 Last Inspection: 03/13/2019 Sticker Expires: 9/13/2019 Standard Deviation: 650.00 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Two Years of Data Slump Greater than or equal to 2 inches

1424543	601.002.015 Concrete, Class K		3.33	3.33	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1424584	601.002.003 Concrete, Class B	03/11/2019	2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last One Year of Data Slump Greater than or equal to 2 inches

1432582	601.002.003 Concrete, Class B	06/07/2019	2.87	2.87	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1455034	601.002.023 Concrete, Class H-IC	10/14/2018	3.46	3.46	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455048	601.002.023 Concrete, Class H-IC	01/27/2019	3.43	3.43	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455075	601.002.003 Concrete, Class B		2.86	2.86	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463274	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463277	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463280	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463283	601.002.013 Concrete, Class H		3.44	3.44	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 08 Plant Name: FCC1.04.601 Fairfax Concrete F-4 @ Thomas WV
 Last Inspection: 03/13/2019 Sticker Expires: 9/13/2019 Standard Deviation: 650.00 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Two Years of Data Slump Greater than or equal to 2 inches

1424542	601.002.015 Concrete, Class K		3.33	3.33	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Two Years of Data Slump Greater than or equal to 2 inches

1424583	601.002.013 Concrete, Class H		3.44	3.44	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last One Year of Data Slump Greater than or equal to 2 inches

1424583	601.002.013 Concrete, Class H		3.44	3.44	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Two Years of Data Slump Greater than or equal to 2 inches

1432580	601.002.003 Concrete, Class B	06/07/2019	2.87	2.87	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last One Year of Data Slump Greater than or equal to 2 inches

1432580	601.002.003 Concrete, Class B	06/07/2019	2.87	2.87	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455033	601.002.023 Concrete, Class H-IC	10/14/2018	3.46	3.46	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455047	601.002.023 Concrete, Class H-IC	01/27/2019	3.43	3.43	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455074	601.002.003 Concrete, Class B		2.86	2.86	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463273	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463276	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463279	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463282	601.002.013 Concrete, Class H		3.44	3.44	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 05

Plant Name: FCC1.05.601

Allegheny Concrete F-5 W Short Gap WV (Transit

Last Inspection: 03/07/2019

Sticker Expires: 9/7/2019

Standard Deviation: 650.00

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1436470	601.002.023 Concrete, Class H-IC	04/02/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455028	601.002.023 Concrete, Class H-IC	09/07/2018	3.46	3.46	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last One Year of Data Slump Greater than or equal to 2 inches												
1461806	601.002.004 Concrete, Class B Modified		3.34	3.34	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last One Year of Data Slump Less than 2 inches												
1461807	601.002.003 Concrete, Class B		2.87	2.87	3							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Greater than or equal to 2 inches												
1461807	601.002.003 Concrete, Class B		2.87	2.87	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Three Months of Data Slump Greater than or equal to 2 inches												
1461807	601.002.003 Concrete, Class B		2.87	2.87	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461808	601.002.015 Concrete, Class K		3.35	3.35	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463284	601.002.013 Concrete, Class H		3.45	3.45	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 09

Plant Name: GRM1.01.601 Greenbrier Ready Mix, Caldwell WV

Last Inspection: 06/07/2019

Sticker Expires: 12/7/2019

Standard Deviation: 650.00

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1459803	601.002.003 Concrete, Class B		2.87	2.87	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1459814	601.002.015 Concrete, Class K		3.35	3.35	1							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Greater than or equal to 2 inches												
1459816	601.002.003 Concrete, Class B		2.87	2.87	2							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						
Last One Year of Data Slump Greater than or equal to 2 inches												
1459816	601.002.003 Concrete, Class B		2.87	2.87	3							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463268	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463270	601.002.013 Concrete, Class H		3.47	3.47	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 10

Plant Name: JRM1.01.601 Jowar Ready Mix @ laeger, WV

Last Inspection: 03/04/2019

Sticker Expires: 9/4/2019

Standard Deviation: 650.00

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1455052 601.002.003
Concrete, Class B

02/28/2019

2.87 2.87

0
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1463261 601.002.003
Concrete, Class B

2.87 2.87

0
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1463262 601.002.015
Concrete, Class K

3.35 3.35

0
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1463339 601.002.003
Concrete, Class B

3.23 3.23

0
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463340	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Three Months of Data Slump Greater than or equal to 2 inches												
1463341	601.002.003 Concrete, Class B		3.23	3.23	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463342	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 10

Plant Name: KCX1.03.601 Kokosing Construction Company F-3 @ Sophia,

Last Inspection: 06/13/2019

Sticker Expires: 12/13/2019

Standard Deviation: 650.00

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463343	501.002.001 Concrete, Pavement		2.87	2.87	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1465017	501.002.001 Concrete, Pavement		2.87	2.87	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 02

Plant Name: LCC1.01.601 Logan Concrete F-1 @ Logan, WV

Last Inspection: 01/29/2019

Sticker Expires: 7/29/2019

Standard Deviation: 650.00

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Two Years of Data Slump Greater than or equal to 2 inches

1455065 601.002.003 **03/22/2019** 2.89 2.89
 Concrete, Class B

4

MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Two Years of Data Slump Less than 2 inches

1455066 601.002.015 **03/21/2019** 3.35 3.35
 Concrete, Class K

1

MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

Last Two Years of Data Slump Greater than or equal to 2 inches

1455066 601.002.015 **03/21/2019** 3.35 3.35
 Concrete, Class K

3

MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1455067 601.002.022 **03/22/2019** 3.74 3.74
 Concrete, Class DC

0

MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455068	601.002.013 Concrete, Class H	03/21/2019	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461782	679.002.002 Concrete, Microsilica		3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461810	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461814	601.002.015 Concrete, Class K		3.36	3.36	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461818	601.002.022 Concrete, Class DC		3.74	3.74	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461850	501.002.001 Concrete, Pavement		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461852	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 01

Plant Name: MRM2.01.601 Logan Concrete, Inc. - Madison Plant @ Madiso

Last Inspection: 01/28/2019

Sticker Expires: 7/28/2019

Standard Deviation: 511.32

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436409	601.002.003 Concrete, Class B		2.87	2.87	10	3000	1.604	3.615	602.93	3967.1	< 4381	< 5179.59
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1436410	601.002.015 Concrete, Class K		3.35	3.35	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436482	601.002.022 Concrete, Class DC		3.74	3.74	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1436483	601.002.004 Concrete, Class B Modified	05/06/2018	3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1455030	601.002.013 Concrete, Class H		3.45	3.45	3							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1461783	679.002.002 Concrete, Microsilica		3.83	3.83	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Greater than or equal to 2 inches

1461811	601.002.003 Concrete, Class B		2.87	2.87	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

Last One Year of Data Slump Greater than or equal to 2 inches

1461811	601.002.003 Concrete, Class B		2.87	2.87	5							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

Last Three Months of Data Slump Greater than or equal to 2 inches

1461811	601.002.003 Concrete, Class B		2.87	2.87	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last One Year of Data Slump Less than 2 inches

1461815	601.002.015 Concrete, Class K		3.36	3.36	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

Last One Year of Data Slump Greater than or equal to 2 inches

1461815	601.002.015 Concrete, Class K		3.36	3.36	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1461819	601.002.022 Concrete, Class DC		3.74	3.74	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1461851	501.002.001 Concrete, Pavement		2.87	2.87	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last One Year of Data Slump Greater than or equal to 2 inches

1461853	601.002.013 Concrete, Class H		3.45	3.45	4							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 01

Plant Name: MRM3.01.601 Mozack Ready Mix, Winfield WV

Last Inspection: 04/02/2019

Sticker Expires: 10/2/2019

Standard Deviation: 580.52

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Less than 2 inches												
1458937	601.002.003 Concrete, Class B		2.87	2.87	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Two Years of Data Slump Greater than or equal to 2 inches												
1458937	601.002.003 Concrete, Class B		2.87	2.87	15	3000	1.549	3.27	620.76	3961.56 <	4563.33 <	5029.89
					MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							
Last One Year of Data Slump Less than 2 inches												
1458937	601.002.003 Concrete, Class B		2.87	2.87	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Greater than or equal to 2 inches												
1458937	601.002.003 Concrete, Class B		2.87	2.87	43	3000	1.5	3	444.17	3666.26 <	4226.05 <	4332.51
					MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Less than 2 inches												
1458938	601.002.015 Concrete, Class K		3.35	3.35	5							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Two Years of Data Slump Greater than or equal to 2 inches												
1458938	601.002.015 Concrete, Class K		3.35	3.35	4							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last Two Years of Data Slump Less than 2 inches

1458994	601.002.003 Concrete, Class B		4.07	4.07	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last Two Years of Data Slump Greater than or equal to 2 inches

1458994	601.002.003 Concrete, Class B		4.07	4.07	4							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1459003	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1459004	601.002.013 Concrete, Class H		3.45	3.21	16	4000	1.543	3.233	578.68	6887.5	> 5870.87	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1459824	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1459825	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463252	601.002.015 Concrete, Class K		3.37	3.37	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463253	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463254	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463255	601.002.003 Concrete, Class B		2.89	2.89	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463256	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

District: 09 **Plant Name:** PCI1.01.601 Pro Contracting INC

Last Inspection: 02/14/2019 **Sticker Expires:** 8/14/2019 **Standard Deviation:** 650.00 **Rating:** A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463295	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 01

Plant Name: RRM1.01.601 Rumble Ready Mix F-1 @ Winfield, WV

Last Inspection: 04/02/2019

Sticker Expires: 10/2/2019

Standard Deviation: 569.78

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last One Year of Data Slump Greater than or equal to 2 inches

1455041 601.002.016 **11/18/2018** 3.35 3.35

Concrete, Class K Modified

2

MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Two Years of Data Slump Greater than or equal to 2 inches

1455099 501.002.002 3.35 3.35

Concrete, Pavement HES

5

MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

Last One Year of Data Slump Greater than or equal to 2 inches

1455099 501.002.002 3.35 3.11

Concrete, Pavement HES

12

3000 1.576 3.429 117.33 8587.5 > 3402.32 = 0.24

DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1458929	601.002.003 Concrete, Class B		2.87	2.87	25	3000	1.511	3.055	728.28	4100.43 <	4808 <	5224.9
					MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26							
Last One Year of Data Slump Less than 2 inches												
1458929	601.002.003 Concrete, Class B		2.87	2.87	4							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last One Year of Data Slump Greater than or equal to 2 inches												
1458929	601.002.003 Concrete, Class B		2.87	2.87	8							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Three Months of Data Slump Less than 2 inches												
1458929	601.002.003 Concrete, Class B		2.87	2.87	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Three Months of Data Slump Greater than or equal to 2 inches												
1458929	601.002.003 Concrete, Class B		2.87	2.87	1							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458931	601.002.022 Concrete, Class DC		3.59	3.59	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458933	601.002.015 Concrete, Class K		3.35	3.35	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458935	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Less than 2 inches												
1458962	601.002.003 Concrete, Class B		2.87	2.87	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last Two Years of Data Slump Greater than or equal to 2 inches												
1458962	601.002.003 Concrete, Class B		2.87	2.87	6							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last One Year of Data Slump Less than 2 inches												
1458962	601.002.003 Concrete, Class B		2.87	2.87	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last One Year of Data Slump Greater than or equal to 2 inches												
1458962	601.002.003 Concrete, Class B		2.87	2.87	6							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458964	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458966	601.002.024 Concrete, Class B w/ Fly Ash		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458968	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458982	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458984	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458988	501.002.002 Concrete, Pavement HES		3.83	3.83	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458990	601.002.022 Concrete, Class DC		3.59	3.59	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 01

Plant Name: RRM1.02.601 Rumble Ready Mix F-2 @ Belle, WV

Last Inspection: 10/05/2018

Sticker Expires: 4/5/2019

Standard Deviation: 650.00

Rating: B

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1455100	501.002.002 Concrete, Pavement HES		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Greater than or equal to 2 inches												
1458930	601.002.003 Concrete, Class B		2.87	2.87	4							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458932	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458934	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458936	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458963	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458965	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458967	601.002.024 Concrete, Class B w/ Fly Ash		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458969	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458983	601.002.013 Concrete, Class H		3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458985	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458989	501.002.002 Concrete, Pavement HES		3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1458991	601.002.022 Concrete, Class DC		3.59	3.59	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

District: 03 **Plant Name:** SCC1.01.601 Smith Concrete F-1 @ Porterfield, OH
Last Inspection: 11/30/2018 **Sticker Expires:** 5/30/2019 **Standard Deviation:** 430.82 **Rating:** B

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Less than 2 inches												
1455069	601.002.003 Concrete, Class B	04/03/2019	2.89	2.89	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last Two Years of Data Slump Greater than or equal to 2 inches												
1455069	601.002.003 Concrete, Class B	04/03/2019	2.89	2.65	41	3000	1.5	3	412.1	4508.29	> 4236.3	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												
Last One Year of Data Slump Greater than or equal to 2 inches												
1455069	601.002.003 Concrete, Class B	04/03/2019	2.89	2.89	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463289	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 03 Plant Name: SCC1.02.601 Smith Concrete F-2 @ Reno, OH
 Last Inspection: 02/19/2019 Sticker Expires: 8/19/2019 Standard Deviation: 650.00 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455070	601.002.003 Concrete, Class B	04/03/2019	2.91	2.91	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463290	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463330	601.002.022 Concrete, Class DC		3.73	3.73	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463333	601.002.009 Concrete, Class C		2.51	2.51	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 09

Plant Name: SSC1.01.601 Superior Supply @ Caldwell, WV

Last Inspection: 06/07/2019

Sticker Expires: 12/7/2019

Standard Deviation: 650.00

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1455077 601.002.003
Concrete, Class B

06/27/2019 2.87 2.87

0
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1459815 601.002.015
Concrete, Class K

3.35 3.35

0
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1459817 601.002.003
Concrete, Class B

2.87 2.87

0
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1463269 601.002.022
Concrete, Class DC

3.59 3.59

0
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor (K_1)	Factor (K_2)	Standard Deviation (s)	Average Strength(X)	(F_c+K_2s)	$X-(F_c+K_1s)/1.4$
1463271	601.002.013 Concrete, Class H		3.47	3.47	0	MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 06

Plant Name: SSC1.03.601 Smith Concrete F-3 @ Tiltonville OH

Last Inspection: 03/18/2019

Sticker Expires: 9/18/2019

Standard Deviation: 639.47

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Three Months of Data Slump Greater than or equal to 2 inches

1463265	601.002.022 Concrete, Class DC		3.73	3.73	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last One Year of Data Slump Greater than or equal to 2 inches

1463266	601.002.022 Concrete, Class DC		4.26	4.26	7							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last Three Months of Data Slump Greater than or equal to 2 inches

1463266	601.002.022 Concrete, Class DC		4.26	4.26	3							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last One Year of Data Slump Greater than or equal to 2 inches

1463293	601.002.004 Concrete, Class B Modified		3.95	3.95	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last Three Months of Data Slump Greater than or equal to 2 inches

1463293	601.002.004 Concrete, Class B Modified		3.95	3.95	6							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last One Year of Data Slump Greater than or equal to 2 inches												
1463329	601.002.003 Concrete, Class B		2.87	2.87	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Three Months of Data Slump Less than 2 inches												
1463329	601.002.003 Concrete, Class B		2.87	2.87	6							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Three Months of Data Slump Greater than or equal to 2 inches												
1463329	601.002.003 Concrete, Class B		2.87	2.63	43	3000	1.5	3	638.02	5695.58	> 4914.06	= 0.24
					DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1463331	601.002.015 Concrete, Class K		3.35	3.35	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Three Months of Data Slump Greater than or equal to 2 inches												
1463332	601.002.004 Concrete, Class B Modified		4.07	4.07	9							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Three Months of Data Slump Greater than or equal to 2 inches

1463337	601.002.006 Concrete, Class B Mass, Modified		3.45	3.45	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1465022	601.002.011 Concrete, Class D		1.11	1.11	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 05 Plant Name: TBH1.01.601 Thomas, Bennet & Hunter, Inc @ Martinsburg, W
 Last Inspection: 03/13/2019 Sticker Expires: 9/13/2019 Standard Deviation: 804.29 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
389014 - R15	601.002.003 Concrete, Class B		2.87	2.63	23	3000	1.515	3.081	798.86	6444.65	> 5461.29	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												
389014 - R15	601.002.003 Concrete, Class B		2.87	2.63	79	3000	1.5	3	858.96	6294.8	> 5576.88	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												
389014 - R15	601.002.003 Concrete, Class B		2.87	2.63	18	3000	1.533	3.175	767.99	5615.89	> 5438.37	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												
389014 - R15	601.002.003 Concrete, Class B		2.87	2.63	33	3000	1.5	3	825.79	5676.36	> 5477.37	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last One Year of Data Slump Greater than or equal to 2 inches												
389016 - R15	601.002.015 Concrete, Class K	01/26/2018	3.37	3.37	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
389017 - R15	601.002.013 Concrete, Class H	01/27/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last Two Years of Data Slump Less than 2 inches												
1398981	601.002.005		2.96	2.96	8							
	Concrete, Class B Mass				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							
Last Two Years of Data Slump Greater than or equal to 2 inches												
1398981	601.002.005		2.96	2.72	16	3000	1.543	3.233	776.56	5933.75	> 5510.62	= 0.24
	Concrete, Class B Mass				DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							
Last One Year of Data Slump Greater than or equal to 2 inches												
1398981	601.002.005		2.96	2.72	12	3000	1.576	3.429	570	5364.17	> 4954.53	= 0.24
	Concrete, Class B Mass				DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26							
Last Three Months of Data Slump Greater than or equal to 2 inches												
1398981	601.002.005		2.96	2.96	6							
	Concrete, Class B Mass				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1399059	601.002.004		2.95	2.95	0							
	Concrete, Class B Modified				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
Last One Year of Data Slump Greater than or equal to 2 inches												
1436432	601.002.013	07/03/2017	3.35	3.35	5							
	Concrete, Class H				MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 06

Plant Name: TSC1.01.601 Tri-Son Concrete Inc F-1 @ Bellaire, OH

Last Inspection: 04/05/2019

Sticker Expires: 10/5/2019

Standard Deviation: 650.00

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last Two Years of Data Slump Greater than or equal to 2 inches

1455031	601.002.003 Concrete, Class B		2.87	2.87	5							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

Last One Year of Data Slump Greater than or equal to 2 inches

1455031	601.002.003 Concrete, Class B		2.87	2.87	3							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1461843	601.002.015 Concrete, Class K		3.35	3.35	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1463285	601.002.013 Concrete, Class H		3.52	3.52	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 02

Plant Name: TWG1.01.601 The Wells Group F-1 @ South Williamson, KY

Last Inspection: 04/23/2019

Sticker Expires: 10/23/2019

Standard Deviation: 650.00

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1394075	601.002.003 Concrete, Class B		2.87	2.87	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1421138	601.002.004 Concrete, Class B Modified	01/27/2018	3.35	3.35	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455013	601.002.015 Concrete, Class K	06/13/2018	3.35	3.35	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455022	601.002.013 Concrete, Class H	08/30/2018	3.45	3.45	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1459000	679.002.002 Concrete, Microsilica		3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461788	601.002.022 Concrete, Class DC		3.74	3.74	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 02

Plant Name: TWG1.02.601 The Wells Group F-2 @ Lovely, KY

Last Inspection: 04/23/2019

Sticker Expires: 10/23/2019

Standard Deviation: 650.00

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
390295 RE-14	601.002.003 Concrete, Class B		2.87	2.87	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1421137	601.002.004 Concrete, Class B Modified	01/27/2018	3.35	3.35	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455014	601.002.015 Concrete, Class K	06/01/2018	3.35	3.35	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455023	601.002.013 Concrete, Class H	08/31/2018	3.45	3.45	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1459001	679.002.002 Concrete, Microsilica		3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461789	601.002.022 Concrete, Class DC		3.74	3.74	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 02 Plant Name: TWG1.03.601 The Wells Group F-3 @ Wayne, WV
 Last Inspection: 05/10/2019 Sticker Expires: 11/10/2019 Standard Deviation: 650.00 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1420224	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1421135	601.002.004 Concrete, Class B Modified	01/27/2018	3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455015	601.002.015 Concrete, Class K	06/02/2018	3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455024	601.002.013 Concrete, Class H	08/30/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1458999	679.002.002 Concrete, Microsilica		3.83	3.83	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461787	601.002.022 Concrete, Class DC		3.74	3.74	0							
						MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 02 Plant Name: TWG1.04.601 The Wells Group F-4 @ Cannonsburg, KY
 Last Inspection: 05/14/2019 Sticker Expires: 11/14/2019 Standard Deviation: 650.00 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1420283	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455016	601.002.015 Concrete, Class K	06/01/2018	3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455025	601.002.013 Concrete, Class H	08/30/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1459002	679.002.002 Concrete, Microsilica		3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor (K_1)	Factor (K_2)	Standard Deviation (s)	Average Strength(X)	(F_c+K_2s)	$X-(F_c+K_1s)/1.4$
1461790	601.002.022 Concrete, Class DC		3.74	3.74	0	MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 02 Plant Name: TWG1.05.601 The Wells Group F-5 @ Louisa, KY
 Last Inspection: 06/25/2019 Sticker Expires: 12/25/2019 Standard Deviation: 650.00 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1421064	601.002.003 Concrete, Class B		2.87	2.87	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1421104	601.002.013 Concrete, Class H	01/27/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1421139	601.002.004 Concrete, Class B Modified	01/27/2018	3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1436456	601.002.003 Concrete, Class B	09/29/2017	3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455017	601.002.015 Concrete, Class K	06/01/2018	3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455026	601.002.013 Concrete, Class H	08/31/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1459804	679.002.002 Concrete, Microsilica		3.83	3.83	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1461791	601.002.022 Concrete, Class DC		3.74	3.74	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 01

Plant Name: VBC1.03.601 Cardinal Concrete @ Robertsburg

Last Inspection: 02/15/2019

Sticker Expires: 8/15/2019

Standard Deviation: 650.00

Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

Last One Year of Data Slump Greater than or equal to 2 inches

1461856	601.002.003 Concrete, Class B		2.87	2.87	2							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	---------------------	----------	----------------

1461857	601.002.015 Concrete, Class K		3.35	3.35	0							
					MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA							

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

District: 06 Plant Name: WIC1.01.601 Weirton Ice & Coal @ Weirton, WV
 Last Inspection: 04/04/2019 Sticker Expires: 10/4/2019 Standard Deviation: 779.91 Rating: A-1

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	Average Strength(X)	(Fc+K2s)	X-(Fc+K1s)/1.4
1455020	601.002.015 Concrete, Class K	08/05/2018	3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Two Years of Data Slump Less than 2 inches												
1455021	601.002.003 Concrete, Class B	08/05/2018	2.87	2.87	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												
Last Two Years of Data Slump Greater than or equal to 2 inches												
1455021	601.002.003 Concrete, Class B	08/05/2018	2.87	2.63	42	3000	1.5	3	842.99	6181.43	> 5528.97	= 0.24
DECREASE CEMENT FACTOR BY 0.24 PER SECTION 3.3 OF MP 711.03.26												
Last One Year of Data Slump Greater than or equal to 2 inches												
1455021	601.002.003 Concrete, Class B	08/05/2018	2.87	2.87	15	3000	1.549	3.27	783.4	4213.49	< 5215.33	< 5561.72
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1455038	601.002.013 Concrete, Class H	10/21/2018	3.45	3.45	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last One Year of Data Slump Greater than or equal to 2 inches

1461844	601.002.013 Concrete, Class H		3.50	3.50	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

Last Three Months of Data Slump Greater than or equal to 2 inches

1461844	601.002.013 Concrete, Class H		3.50	3.50	2							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

1461858	601.002.015 Concrete, Class K		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
-------------------	------------------------------	--------------	------------------------	------------------------	----------------	---------------------	-------------	-------------	------------------------	----------	---------------------	----------

Last One Year of Data Slump Greater than or equal to 2 inches

1463244	601.002.003 Concrete, Class B		2.87	2.87	21	3000	1.521	3.112	852.68	4296.93 <	4860.95 <	5653.54
MAINTAIN CURRENT CEMENT FACTOR, PER SECTION 3.3 OF MP 711.03.26												

Last Three Months of Data Slump Greater than or equal to 2 inches

1463244	601.002.003 Concrete, Class B		2.87	2.87	5							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463245	601.002.022 Concrete, Class DC		3.35	3.35	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463263	601.002.022 Concrete, Class DC		3.73	3.73	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
Last Three Months of Data Slump Greater than or equal to 2 inches												
1463264	601.002.022 Concrete, Class DC		4.26	4.26	1							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(Fc)	Factor (K1)	Factor (K2)	Standard Deviation (s)	(Fc+K1s)	Average Strength(X)	(Fc+K2s)
1463294	601.002.004 Concrete, Class B Modified		3.95	3.95	0							
MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA												

PCC Plant Evaluation with Cement Factors

Effective Date: 7/12/2019

<----- Evaluation of Cement Requirements ----->

Mix Design Number	Material Code / Class of Mix	Expired Date	Approved Cement Factor	Adjusted Cement Factor	Pieces of Data	Design Strength(F_c)	Factor ($K1$)	Factor ($K2$)	Standard Deviation (s)	(F_c+K1s)	Average Strength(X)	(F_c+K2s)
1463338	601.002.006 Concrete, Class B Mass, Modified		3.45	3.45	0	MAINTAIN CURRENT CEMENT FACTOR, INSUFFICIENT AMOUNT OF DATA						